

## بسمه تعالی

جدول مقایسه خواص چسب C301 شرکت مواد آلی البرز و چسب Sikadur 330 شرکت Sika

property	Manapar C301	Sikadur 330
colour	White/Gray	White/Gray
Density	1.4 gr/ cm <sup>3</sup>	1.3 gr/ cm <sup>3</sup>
Tensile strength	32 MPa	33.8 MPa
Elongation at break	2%	1.2 %
Tensile adhesion strength	~5.5 MPa	≥ 4 MPa
Tg	60 °C	58 °C
HDT	49 °C	50 °C
Service temperature	-40°C to +45°C	-40°C to +45°C
Mixing ratio	100:40	100:25
Pot life(thin layer)	60 min	57 min
Cure time	4-5 hours	4-5 hours
Viscosity (at 25 °C)	Paste	Non-sag paste

# ManaPar