### COMPOSITES

# Datasheet Coremat<sup>®</sup>**Xi**

The cost effective solution for open mould processesIs used as core material and/or print blocker

■ Is suitable for hand lay-up and spray-up processes

Marine: hulls, decks and structures of boats and yachts

Mass transit: interior and exterior of trains, light rail

Leisure: kayaks, surfboards, pools and tubsIndustrial: cladding panels, containers and tanks

Transportation: parts and panels of cars, trailers and trucks

Keep Coremat<sup>®</sup> Xi away from direct sunlight, therefore store Coremat<sup>®</sup> Xi in the original bag. This will ensure proper functioning of the resin indicator. Please note that the resin indicator is not a guarantee that sufficient resin has been applied, but strictly a control mechanism to identify dry

Applications Lantor Coremat<sup>®</sup>Xi

spots. Always check resin content.

 Is a polyester nonwoven and compatible with all regular types of resins, including Polyester, Vinylester, Phenolic

Lantor Coremat<sup>®</sup>Xi

and Epoxy

and buses

Notification

#### The information contained in this document has been compiled in good faith by Lantor BV, but nevertheless no representation or warranty is given as to the accuracy or completeness of the (technical) information provided herein. Lantor BV can not be held liable of any damages arising from any (printing) errors or omissions in this information. Lantor BV reserves the right to make changes with respect to the information provide at any time without further notice.

### Dimensional data

Properties		Xi 1	Xi 2	Xi 3	Xi 4	Xi 5
Thickness	mm	1,4	2,0	3,0	4,0	5,0
Roll length	m	130	80	50	40	30
Roll width	m	1	1	1	1	1
Resin uptake	kg/m²	0,8	1,2	1,8	2,4	3,0
Dry weight	g/m²	45	55	80	105	125
Density impregnate	ed kg/m³	630	630	630	630	630

## Typical mechanical properties of Lantor Coremat<sup>®</sup>Xi<sup>\*</sup> impregnated with unsaturated polyesther resin

Mechanical properties	unit	value	test method	
Flexural strength	MPa	11	ASTM D790	
Flexural modulus	MPa	1100	ASTM D790	
Tensile strength across layers	MPa	4	ASTM C297	
Compression strength: 10% strain	MPa	10	ISO 844	
Shear strength	MPa	5	ASTM C273-61	
Shear modulus	MPa	35	ASTM C273-61	
*Lantor Coremat®Xi 3				

# Coremat<sup>®</sup>Xi



## Core material and print through barrier for open mould processes

- Blue resin indicator
- Excellent impregnation
- Improved control

### Information

PO box 45 - 3900 AA Verlaat 22 - 3901 RG Veenendaal The Netherlands T +31(0) 318 537 111 composites@lantor.com







enabling performance www.lantor.com